

## SUPAFIL® CARBONPLUS (FOR DOUBLE BRICK MASONRY CAVITIES)

October 2018



### APPLICATIONS



### DESCRIPTION

Supafil® CarbonPlus is designed for installation into existing and new double brick masonry cavities. Supafil® CarbonPlus is an unbonded, non-combustible glasswool product which requires no mixing on site. Supafil® CarbonPlus is specifically designed to be used in existing masonry cavity walls with a minimum cavity width of 40mm. CodeMark™ certification for Supafil® CarbonPlus approves the application and installation procedure for this product. The product is for use in existing and new masonry cavity walls, subject to the conditions detailed in CodeMark™ certificate GM-CM30057.

### PERFORMANCE

#### Thermal

Thermal conductivity (AS/NZS 4859.1):

R-1.3 @ 50mm, 25kg/m<sup>3</sup>.

#### Fire Hazard Properties

Ignitability: 0, Spread of Flame: 0, Heat Evolved: 0, Smoke Developed: 1.

#### Vapour Resistivity

Water vapour resistivity:

5.00 MN. s.g.m.

#### Microbial Growth

Does not support microbial growth.

#### Corrosion Resistance

No greater than sterile cotton.


#### Combustibility

Non-combustible.

### BENEFITS

- ✓ Maximum performance in walls
- ✓ Interior and exterior install methods
- ✓ Silicone treated for extra moisture protection
- ✓ Sustainable - each bag contains the equivalent of over 45 recycled glass bottles
- ✓ Fast, easy installation by Approved Installers

### CERTIFICATION



## SUPAFIL® CARBONPLUS (FOR DOUBLE BRICK MASONRY CAVITIES)

October 2018

### ADDITIONAL INFORMATION

#### Specification Guide

The cavity wall insulation shall be Supafil® CarbonPlus, 0.039 W/mK, 25kg/m<sup>3</sup>, CodeMark™ certified to meet the provisions of the Australian Building Code. The product will be non-combustible, CFC/HCFC free, zero ODP and GWP, silicone treated glasswool insulation with high post-consumer recycled glass content. It will be manufactured under Quality Assurance Standards ISO 9001:2008 and ISO 14001:2004 by Knauf Insulation and shall be installed in accordance with the instructions issued by them.

#### Permanence

- Non-combustible, non-corrosive.
- Will not rot, mildew or deteriorate.
- Silicone treated for continued durability in high moisture areas.

#### Durability

- Silicone treated for extra moisture protection.

#### Noise reduction

- Supafil® CarbonPlus reduces sound passing through cavity walls.

#### Energy conservation

- Reduces fuel usage and utility bills for heating and air conditioning.

#### Thermal performance

The stated thermal resistance (R-Value) is provided by installing the required density at the thickness (per the manufacturer's instructions).

Supafil® CarbonPlus is designed to be installed at a minimum density of 25kg/m<sup>3</sup>. Supafil® CarbonPlus will achieve a thermal conductivity of 0.039W/mK. When installed at various thicknesses Supafil® CarbonPlus will contribute to the thermal requirements for masonry cavity walls and of the Australian Building Code.

Supafil® CarbonPlus when installed at the target density and at 50mm thick will contribute R1.3 to the wall system. In standard masonry walls with an overall thickness of 230mm the wall will achieve an estimated R1.9 total system value.

Supafil® CarbonPlus is not designed for mixing with other products, adhesives or binder systems as these may affect the thermal performance and is not recommended by the manufacturer.

#### Gaps, voids and penetrations

Supafil® CarbonPlus fills all gaps and voids around service penetrations such as water pipes and electric wiring and any other obstructions or unusual design details, ensuring thermal and acoustic performance is created. Supafil® CarbonPlus allows quicker and more efficient filling of wide cavities where multiple layers of conventional insulation would normally be installed. Supafil® CarbonPlus saves installation time by minimising the steps needed to fully insulate tight corners and hard to reach areas.

## SUPAFIL® CARBONPLUS (FOR DOUBLE BRICK MASONRY CAVITIES)

October 2018

### ADDITIONAL INFORMATION (CONT.)

#### Packaging

Supafil® CarbonPlus is packaged in a strong, poly bag that offers excellent protection from abuse, dust and moisture. Knauf Insulation packages stack without slipping and are easy to handle and store.

#### Australia National Construction Code Series (NCC 2016) Building Code of Australia (BCA)

- CP1/CP2/CP4 and P2.3.1 – Fire Resistance.
- FP1.4 / P2.2 and FP 1.5 / 2.2.3 - Weatherproofing and Dampness.
- FP5.5 / FP5.3 and P2.4.6 – Sound Insulation.
- GP2.1 and P2.3.3 – Heating Appliances.
- JP1 and P2.6.1 – Energy Efficiency.
- Supafil® CarbonPlus thermal resistance has been determined by AS/NZS 4859.1. and will contribute to meeting these requirements.

### SPECIFICATIONS

R-Value (m <sup>2</sup> K/W)	Installed density (kg/m <sup>3</sup> )	Thermal conductivity (W/mK)	Cavity width (mm)	Minimum bag usage rate (bags per 100m <sup>2</sup> )
1.3	25	0.039	50	8.0
1.9	25	0.039	75	12.0
2.6	25	0.039	100	16.0

#### Knauf Insulation Ltd

1/44 Borthwick Avenue,  
Murarrie, Queensland, 4172, Australia

Customer Service: 1800 562 834

Technical Advisory Centre: +61 7 3393 7300

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof. The publisher and editors will be grateful for improvement suggestions and details of possible errors pointed out.

KIAU1017629DS

challenge.  
create.  
care.